


REFLECTIVE FABRIC



RF 500

Rev. 08 dated 19/03/20

GENERAL CHARACTERISTICS



The product basically consists of a fabric coated with metallised microspheres having known reflective index and extremely high refraction power, by means of a polyurethane binder with high flexibility and resistance to mechanical and chemical-physical stresses.

RETROLUX RF 500 is a reflective fabric designed for:

- offer a high resistance of the clothing to repeated domestic washings
- improve the retro-reflection on clothing in conditions of poor visibility

PRODUCT COMPOSITION

Front coating:Glass microspheres metallisedBinder:Aliphatic polymerising polyurethane resin.Substrate:Polyester/Cotton fabric with high dimensional stability.

40% of total weight 22% of total weight 38% of total weight

<u>COEFFICIENT OF RETROREFLECTION*</u> (Cd/lux·m²)

	Entrance Angle			
Observation Angle	5°	20 °	30 °	40 °
12'	519-525	542-551	374-442	176-234
20'	330-360	338-366	300-316	159-201
1 °	29-44	28-37	22-25	26-39
1 ° 30'	13-18	10-11	13-21	8-9

*The values were obtained from an average of various sets of samples. Reflected colur: white.

<u>The silver grey reflective fabric called RETROLUX RF 500 satisfies all the minimum</u> requirements accordingly EN 20471





REFLECTIVE FABRIC

RF 500

Rev. 08 dated 19/03/20

PHYSICAL PERFORMANCE

RETROLUX RF 500 meet or exceed the minimum reflective values after the following test:

- 1. Flexing (ISO 7854/A 7500 cycles)
- 2. Cold Fold (ISO 4675 20 °C)
- 3. Abrasion (UNI 530/2 5000 cycles)
- 4. Temperature variance (12 hours at 50 ℃, 20 hours at –30 ℃)
- 5. Rainfall test (Annex A, ANSI ISEA 107-99 Annex A)

WASHING PERFORMANCES

RETROLUX RF 500 exceed the minimum reflective values after:

60 cycles at 60 °C (ISO 6330)

30 cycles of dry cleaning (ISO 3175-method 9.1)

Wash guideline



Minimum temperature: 30 ℃ Maximum temperature: 62 ℃

Detergent: Use only ECE type A without perborates



- <u>Optical brightness, perborates or additional bleaches, reduces washing performances of Retrolux RF</u> <u>500.</u>
- Do not use organic solvents, chlorine bleaches and alkaline products (pH>8).
- Do not exceed 62 °C during wash
- Do not exceed 120 °C during drying





Rev. 08 dated 19/03/20

Drying Conditions

REFLECTIVE FABRIC

- Air drying is recommended
- TUMBLE DRY: NOT EXCEED 90 ℃
- TUNNEL DRY: 100 °C is recommended, not exceed 120 °C.

Dry cleaning



Use pure Perchloroethylene

ADDITIONAL INFORMATION

The material is supplied in rolls of 50 linear meters length and in all widths from 1 centimeter till 1 meter.

The cut tolerance is ± 1.5 mm.for

For cutting die cutting is recommended. Reflective fabric can also be hand-cut or guillotined.

Sewing: 100% polyester yarn is recommended.

IRONING: Use cool IRON (110℃)



PRINTABILITY

The product correctly transferred and in any case without the front liner, can be printed using inks suitable for polyester or other inks, carrying out preliminary adhesion tests.

We recommend the application of the ink with screen printing technique, good results have been obtained with digital printing with ecosolvent inks.

The correct adhesion of the inks must also be verified by subjecting the printed product to repeated washing.

STORAGE

Retrolux reflective transfer must de stored in a cool and dry area, we recommend temperatures between 15 and 25 $^{\circ}$ C and relative humidity less than 70%.

Retrolux reflective transfer must be stored in their original box and used within 1 year of receipt.

FOR FURTHER INFORMATION CONTACT IRC S.p.A - Italy

Laboratory Manager